

VINEYARD WIRE

VINEYARD WIRE											
Diameter			Break Strength			Tensile Strength			Length	Weight Per Coil LBS.	Coils Per Bundle
Wire Gauge	Inches	mm	Soft	High-Tensile	Extra High-Tensile	Soft	High-Tensile	Extra High-Tensile	Linear Feet/cst.		
9	0.148	3.77	860	2,925	3,441	70,000	170,000	200,000	1,705'	100	5
10	0.135	3.43	787	2,433	2,863	70,000	170,000	200,000	2,057'	100	5
11	0.121	3.06	690	1,935	2,300	70,000	170,000	200,000	2,582'	100	5
12	0.106	2.68	529	1,500	1,765	70,000	170,000	200,000	3,369'	100	5
12.5	0.099	2.51	462	1,309	1,540	70,000	170,000	200,000	3,825'	100	5
13	0.092	2.32	399	1,130	1,330	70,000	170,000	200,000	4,478'	100	5
14	0.080	2.03	352	903	1,036	70,000	170,000	200,000	5,858'	100	5